

## 【Summary】

Researchers use plate seals to cover well plates. Therefore, one of criteria for moderate plate seals is resistance to solvents used for experiments and analysis. We compared the organic solvent resistance, such as methanol, acetonitrile and DMSO, between RAPID EPS and conventional plate seals, such as Seal A, B and C. The evaluation was based on LC/MS (microTOF, Bruker Daltonics) of each eluent after soaking each seal in the solvents. Results clearly showed higher organic solvent resistance of RAPID EPS over conventional seals. The difference was due to siloxane elution out of silicon based adhesive of conventional seals. On the other hand, RAPID EPS used synthetic rubber adhesive instead of silicon adhesive.

## 【Method】

A piece of each plate seal was placed in a 1.5ml tube for soaking in organic solvents such as MeOH, AcCN, DMSO. The tubes were incubated for 6 days after vortex and sonication. For LC/MS analysis, three samples from each tube were analyzed (see Figure 1).

### HPLC Condition

- Mobile A : Water
- Mobile B : MeOH
- Column : RP-C18, 2.0 x 50 mm
- Column oven : 40 °C
- Flow rate : 0.3 mL/min
- Gradient : 0/10 – 2/10 – 10/95 – 15/95 – 16/10 – 25/10 (min/%B)
- Injection volume : 2 uL

### MS Condition

(microTOF II, Bruker Daltonics)

- Ion source : ESI source
- Mode : Positive Full scan mode

< Figure 1 : Diagram of experiment >



